

PRODUCT DATA SHEET

Sikagard®-62

2-PART EPOXY PROTECTIVE COATING / LINING SYSTEM

DESCRIPTION

Sikagard®-62 is a two part, rigid, 100 % solids, coloured high build epoxy resin based protective coating with high resistance to abrasion and chemical attack.

USES

Sikagard®-62 may only be used by experienced professionals.

- Chemical resistant protective layer on concrete, stone, cementitious mortars and renderings, epoxy cement, epoxy resin based products and steel
- Lining in storage tanks and silos
- Anti-corrosion for chemical bunded areas, food and beverage processing plants, sewage works, water retaining structures, chemical and pharmaceutical facilities.

CHARACTERISTICS / ADVANTAGES

- Solvent free
- Good mechanical and chemical resistance
- High build
- Impervious to liquids
- Easy to mix and to apply

PRODUCT INFORMATION

Composition	Epoxy resin	
Packaging	Part A	8.4 kg
	Part B	3.0 kg
	Sikafloor Pigment x 1	1.15kg
	Total kit 12.55kg - 9.2 L	Total kit 12.55kg - 9.2 L
Appearance / Colour	RAL colour range - refer to Sika colour chart	
Shelf life	Part A: 24 months	
	Part B: 24 months	
	From date of production if stored properly.	

Storage conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C. Protected from direct sunlight.		
Density	Mixed resin ~1.37 kg/l Density values determined at +23 °C		
Solid content	~ 100 %		

TECHNICAL INFORMATION

Shore D Hardness	~80			(DIN 5305)
Mechanical Resistance	Taber Abraser	CS 10/ 1000/ 1000	24.4mg	(ASTM D 4060)
	Taber Abraser	CS 17/ 1000/ 1000	70 mg	
	Taber Abraser	H 22/ 1000/ 1000	560.6mg	
Tensile Adhesion Strength	> 1.5 N/mm ² to concrete			(ISO 4624)
Chemical Resistance	Please contact Sika technical service for specific information.			
Temperature Resistance	Exposure	Dry heat		
	Permanent	+50 °C		
	max. 7 days	+80 °C		
	max. 12 hours	+100 °C		

SYSTEMS

Systems	Standard Three Coat System: (DFT from 600um - 800um)		
	<i>Primer:</i> Sikafloor 160 or 161 + <i>1st Coat:</i> Sikagard 62 + <i>2nd Coat:</i> Sikagard 62		
	Fibreglass Laminate System: (DFT from 1000um - 1200um) Subject to glass Thickness		
	<i>Primer:</i> Sikafloor 160, Fibreglass, Sikafloor 160 + <i>1st Coat:</i> Sikagard 62 + <i>2nd Coat:</i> Sikagard 62		
	SikaGard EpoCem 720 System: (DFT from 1200um +) Subject to EpoCem 720 Thickness		
	Typically used on High Wear, Damaged or High moisture content substrate applications: SikaGard EpoCem 720 + <i>1st Coat:</i> Sikagard 62 + <i>2nd Coat:</i> Sikagard 62 Please refer to Sikagard 720 EpoCem PDS Please refer to individual Product Data Sheets and consult the Sika Technical Department for specific Consumption Priming and Coverage Information pertaining to project requirements.		

APPLICATION INFORMATION

Mixing Ratio	Part A : Part B = 3 : 1 by weight	2.1 : 1 by volume
Consumption	~0.25 - 0.35 L m ² per layer depending on system structure requirements	
Layer Thickness	~0.2 - 0.3 mm per layer depending on substrate condition, method application and temperature. Recommended number of coats - minimum 2 and possibly 3 depending on required film build for the given environment.	
Ambient Air Temperature	+8 °C min. / +40 °C max.	
Relative Air Humidity	< 80 %	
Substrate Temperature	+8 °C min. / +40 °C max. Minimum 3 °C above dew point, beware of condensation	

Pot Life	Temperature		Time	
	+10 °C		~30 min	
	+20 °C		~20 min	
	+30 °C		~10 min	

Waiting Time / Overcoating	Temperature		Min.	Max.	Full cure
	+10 °C		~ 30 hours	~ 3 days	~ 14 days
	+20 °C		~ 10 hours	~ 2 days	~ 10days
	+30 °C		~ 6 hours	~ 1 day	~ 5 days

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must be sound, clean, dry, free from contaminants such as dirt, grease, oil, old coatings, release agents, laitance and other adhesion preventing or influencing substances.

On high absorbent, non-sound or non cement based substrates precautions have to be taken and a suitable primer has to be used.

SUBSTRATE PREPARATION

Concrete Substrate

Concrete substrate must be prepared mechanically to achieve an open textured surface.

Weak areas in the substrate must be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Open voids and blowholes need to be closed with a suitable Sika® pore filling mortar. The roughness of the substrate needs to be levelled with a suitable Sika® rendering and levelling mortar.

Steel Surface

Steel surface must be prepared mechanically using abrasive blast cleaning. The level SSPC-SP 10 "near white metal blast cleaned" or level Sa 2 ½ according to ISO EN 12944-4 has to be achieved. Welds and joints have to be prepared according to EN 14879, part 1. After blast cleaning remove all dust dirt and blasting material. In order to maintain the surface conditions after blast cleaning air-conditioning is recommended.

MIXING

Prior to mixing stir Part A mechanically then add required pigment and stir for a further 1 minute, Add all Part B to Part A and mix for a further 3 minutes until a uniform mix has been achieved. Use a low speed electrical stirrer (300–400 rpm) to avoid air entrapment. To ensure proper mixing pour material into a clean container and stir again.

APPLICATION

Apply by brush, roller or airless spray.

CLEANING OF EQUIPMENT

Clean all tools with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

IMPORTANT CONSIDERATIONS

- Do not apply Sikagard®-62 on moist substrates
- Sag resistance on vertical surface is approx. 200 µm.
- Freshly applied Sikagard®-62 must be protected from damp, condensation and water for at least 24 hours
- For exact colour matching ensure using material from the same control batch numbers.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48



Product Data Sheet

Sikagard®-62

November 2019, Version 04.02

020606010010000001

Sikagard-62-en-AU-(11-2019)-4-2.pdf

